



## Technical Information

---

Product name	:	MoTip Removable Lacquer			
Colour High Gloss	:	Black	White	Carbon	Green
Article number	:	04302	04303	04304	04305
Colour High Gloss	:	Orange	Transparent	Blue	Red
Article number	:	04306	04307	04308	04309
Colour	:	Black matt	Fluor Yellow		
Article number	:	04301	04310		
Supplier / Producer	:	MOTIP DUPLI B.V. Wolfraamweg 2 NL-8471 XC WOLVEGA			
		Telephone number	+31 561 – 69 44 00		
		Telefax number	+31 561 – 69 44 31		

---

### Product description

Special lacquer to create a removable lacquer film. Suitable to treat smooth, non-absorbing surfaces, like blank metal, aluminium, glass and surfaces treated with 2K lacquers. Not suitable for surfaces treated with 1K lacquer systems.

### Product characteristics

Fast drying  
Good filling property  
Resistant to chemicals and weather influences  
360° valve

### Physical and Chemical Characteristics

Contents	:	500 ml
Base	:	Synthetic rubber
VOC-content	:	Approximately 92% w/w
Solid content	:	Approximately 8% w/w
Coverage	:	0,2 to 0,4 m <sup>2</sup> when applying 5 layers.
Dust dry	:	After approximately 10 minutes
Tack free	:	After approximately 30 minutes
Removable	:	After 2 hours
Heat resistant	:	To 100°C

### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

#### Pre Treatment

Clean the surface, do not sand. The surface should be clean, dry and free of grease. Do not apply any primer.

#### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C at a relative humidity of <65%. Before use, shake the aerosol for 3 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply at least 5 layers removable lacquer, with an interval of 5 minutes. To avoid cracking of the film when removing this, apply an extra layer at critical spots (corners and edges).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**